

676154PS Special UV Mouse Pad Non-slip Clear is intended to provide a rubbery, semi-tacky surface that resists slipping.

The Spl UV Mouse Pad Clear may be printed over the following Nazdar ink systems: 1600 Series, 1900 Series, 3400 Series, 3500 Series, 3600 Series and 3900 Series.

SUBSTRATES Polycarbonate, Top-coated or Primed Polyester, Vinyl

USER INFORMATION

While technical information and advice on the use of this product is provided in good faith, the User bears sole responsibility for selecting the appropriate product for their end-use requirements. See full disclaimer at the end of the document.

MESH 60-305 threads per inch (25-120 threads per cm) monofilament polyester mesh for most applications

COVERAGE 1000 to 1800 square feet per gallon, depending on mesh used

STENCIL Solvent resistant, UV ink compatible direct emulsions and capillary films

SQUEEGEE 60-70 durometer polyurethane squeegee

PRINTING 676154PS UV Clear is formulated to be press ready. Thoroughly mix the ink prior to printing.
 The ink cures with a tacky surface, therefore, applying a protective covering or slip sheet over the cured ink is necessary for the printed pieces to stack.
 Maintain ink temperature at 65°-90° F (18°-32° C) for optimum print and cure performance.
 Pretest to determine optimum printing performance for a particular set of ink, substrate, screen, press, and curing variables/conditions.
 The ink can be affected by stray UV light. Be aware of skylights, windows and overhead lights curing the ink in the screen. Leaving a container uncovered may result in the ink’s surface forming a “skin,” caused by reaction with room lighting or other stray lights. Keep containers covered. Light filters are recommended.

CURE PARAMETERS 676154PS cures when exposed to a medium pressure mercury vapor lamp set at 200 watts per inch (80 W /cm) with millijoules (mJ) and milliwatts (mW) of:
 150 - 200 mJ/cm² @ 600+ mW/cm²
 These guidelines are intended only as a starting point for determining cure parameters, which must be determined under actual production conditions.

CLEAN UP Screen Wash (Prior to Reclaim): Use IMS203 Economy Graphic Screen Wash or IMS207C Graphic Recirculating Wash.
Press Wash (On Press): Use IMS301 Premium Graphics Press Wash.

STORAGE Store tightly covered at temperatures between 65°-90° F (18°-32° C). Ink taken from the press should not be returned to the original container; store separately to avoid contaminating unused ink.

GENERAL INFORMATION

INK HANDLING Wear gloves and barrier cream to prevent direct skin contact. Safety glasses are suggested in areas where ink may be splashed. If ink does come in contact with skin, wipe ink off with a clean, dry cloth (do not use solvent or reducer). Wash the affected area with soap and water. Consult the Material Safety Data Sheet for further instructions and warnings.

676154PS is a one-part, 100% solids UV-curable screen printing ink which does not contain N-vinyl-2-pyrrolidone (trade name V-Pyrol®).

ADHESION TESTING This ink is intended to produce a “grabby”, tacky surface. The definition of proper cure and adhesion will vary, depending on the end use. Test appropriately.

PRODUCT OFFERING

PACKAGING 676154PS Special UV Mouse Pad Non-Slip Clear is available in 1-gallon containers. Cleaners are available in 1-gallon, 5-gallon, and 55-gallon containers.

Stock Number	Cleaners
IMS203	Economy Graphic Screen Wash
IMS207C	Graphic Recirculating Wash
IMS301	Premium Graphic Press Wash

Nazdar® stands behind the quality of this product. Nazdar® cannot, however, guarantee the finished results because Nazdar® exercises no control over individual operating conditions and production procedures. While technical information and advice on the use of this product is provided in good faith, the User bears sole responsibility for selecting the appropriate product for their end-use requirements. Users are also responsible for testing to determine that our product will perform as expected during the printed item’s entire life-cycle from printing, post-print processing, and shipment to end-use. This product has been specially formulated for screen printing, and it has not been tested for application by any other method. Any liability associated with the use of this product is limited to the value of the product purchased from Nazdar®.

Based on information from our raw material suppliers, these products are formulated to contain less than 0.06% lead. If exact heavy metal content is required, independent lab analysis is recommended.

Nazdar Worldwide Headquarters
 8501 Hedge Lane Terrace, Shawnee, KS 66227-3290 USA
 Toll Free: 866.340.3579 or Tel: 913.422.1888 Fax: 913.422.2296
 e-mail: custserv@nazdar.com

Nazdar Limited
 Barton Road, Heaton Mersey, Stockport, England SK4 3EG
 Tel: + (44) 0.161.442.2111 Fax: + (44) 0.161.442.2001
 e-mail: technicalservicesuk@nazdar.com

<http://www.nazdar.com>